中国认可
国际互认
检测
TESTING
CNAS L1978

190000122473

检 测 报 告
TEST REPORT

报 告 编 号:
REPORT NO. : 25202104750

样 品 名 称:
NAME OF SAMPLE: 通体大理石瓷砖
PORCELAIN TILE

委 托 单 位:
APPLICANT: 青岛东泰烜贸易有限公司
QINGDAO ORIENTAL BRIGHT TRADING CO.,LTD.

检 验 日 期:
DATE OF TEST: 22/11/2021 – 30/11/2021(dd/mm/yy)

国 家 建 筑 卫 生 陶 瓷 检 测 重 点 实 验 室
STATE KEY TESTING LABORATORY OF BUILDING CERAMICS AND SANITARY WARE
佛 山 海 关 综 合 技 术 中 心
COMPREHENSIVE TECHNOLOGY CENTRE OF FOSHAN CUSTOMS

佛 山 海 关 综 合 技 术 中 心
COMPREHENSIVE TECHNOLOGY CENTRE OF FOSHAN CUSTOMS

检 测 报 告
TEST REPORT

报告编号：25202104750
Report No:

样品名称 Name of sample	通体大理石瓷砖 PORCELAIN TILE	名义尺寸 Nominal size (N)	120cm×60cm
表面特性 Nature of the surface	有釉砖 Glazed (GL)	工作尺寸 Work size (S_w)	1200mm×600mm×11.9mm
类别 Group	B Ⅰa	用途 Application	釉面室内外墙地砖
样品标记 Mark of samples	品牌：奢伦娅 BRAND: SARENIA	样品数量 Quantity of samples	30 块 30 Pieces
委托单位 Applicant	青岛东泰烜贸易有限公司 QINGDAO ORIENTAL BRIGHT TRADING CO.,LTD.	委托单位地址 Address of applicant	山东省青岛市市南区山东路 8 号丁 3 号楼 3308 ROOM 3308, BUILDING 3, NO.8 SHANDONG ROAD, SHINAN DISTRICT, QINGDAO
委托单位电话 Telephone of applicant	86-13615329235	委托单位传真 Fax of applicant	—
样品来源 Source of Samples	委托单位自送样品 Samples selected by applicant	接样日期 Received on	22/11/2021
检验依据 Test Standard	GB/T 4100-2015《陶瓷砖》附录 G 干压陶瓷砖（E≤0.5% B Ⅰa 类）		
检验结果 Results of Test	样品经检验,所检验项目的检验结果符合 GB/T 4100-2015 标准中附录 G 的规定。 The results conform to the requirement of Annex G of standard GB/T 4100-2015 with respect to the test items.		
检验单位盖章 Stamp of Test Unit	日期：03/12/2021 Date:	检验单位联系方式 Address of Test Unit	地址：广东省佛山市禅城区魁奇一路澜石（国际）金属交易中心十八座二楼 Address： 2/F, Building 18, Lanshi International Metal Exchange Center, Kuiqiyi Road, Chancheng District, Foshan, Guangdong, China (528000) 电话（Tel）：86-757-83960558 86-757-83827991 传真（Fax）：86-757-83827971 邮箱（E-mail）：fsiqtc@163.com
声明 Notes	1、我们已尽所知所能实施上述检验，不能因签发本报告而免除有关各方根据合同和法律所承担的责任和义务； All inspections are carried out conscientiously to the best of our knowledge and ability. This report does not in any respect absolve the other related parties from his contractual and legal obligations. 2、未经本实验室书面许可，不得部分复制本报告； This report shall not be reproduced, except in full, without the prior written approval from the issuing laboratory. 3、本报告仅是样品的检测结果。 The results in this report apply to the samples only. 4、本报告所述的样品信息为委托单位自行声明，实验室不负责其真实性。 The product information are declared by applicant, and laboratory is not responsible for the authenticity.		

检验 Tested by _____ 审核 Inspected by _____ 批准 Approved by _____

GB/T 4100-2015 《陶瓷砖》附录 G 干压陶瓷砖（$E \leq 0.5\%$ BⅠa类）

条款 Clause	性能 Properties	检验方法 Test Method	要求 Requirements		检验结果 Results	判定 Verdicts
表 G.1 Table G.1	**尺寸和表面质量** **Dimensions and surface quality**					
	长度 **Length** 每块砖的平均尺寸相对于工作尺寸的允许偏差 The deviation,of the average size for each tile (2 sides) from the work size	GB/T 3810.2-2016	N≥150mm	±0.6%	-0.03%~-0.02%	P
				±2.0mm	-0.3mm~-0.2mm	P
	宽度 **Width** 每块砖的平均尺寸相对于工作尺寸的允许偏差 The deviation,of the average size for each tile (2 sides) from the work size	GB/T 3810.2-2016	N≥150mm	±0.6%	-0.01%~+0.02%	P
				±2.0mm	-0.1mm~+0.1mm	P
	厚度 **Thickness** 每块砖厚度的平均值相对于工作尺寸的最大允许偏差 The deviation of the average thickness of each tile from the work size thickness	GB/T 3810.2-2016	N≥150mm	±5%	-1.0%~+0.1%	P
				±0.5mm	-0.1mm~0	P
	边直度: 相对于工作尺寸的最大允许偏差 **Straightness of sides** The maximum deviation from straightness related to the corresponding work sizes					
	长度 Length	GB/T 3810.2-2016	N≥150mm	±0.5%	-0.01%~0	P
				±1.5mm	-0.1mm~0	P
	宽度 Width	GB/T 3810.2-2016	N≥150mm	±0.5%	+0.01%~+0.02%	P
				±1.5mm	0~+0.1mm	P
	直角度: 相对于工作尺寸的最大允许偏差 **Rectangularity** The maximum deviation from Rectangularity related to the corresponding work sizes					
	长度 Length	GB/T 3810.2-2016	N≥150mm	±0.5%	+0.01%~+0.03%	P
				±2.0mm	+0.2mm~+0.4mm	P
	宽度 Width	GB/T 3810.2-2016	N≥150mm	±0.5%	-0.05%~0	P
				±2.0mm	-0.3mm~0	P
	表面平整度: 最大允许偏差 **Surface flatness**: The maximum deviation from flatness	GB/T 3810.2-2016	N>600mm	≤2.0mm	+0.1mm~+0.3mm	P
	表面质量 **Surface quality**	GB/T 3810.2-2016	至少有 95%的砖其主要区域无明显缺陷 A minimum of 95 % of the tiles are to be free from visible defects which can impair the appearance of a major area of tiles		100%	P

佛 山 海 关 综 合 技 术 中 心
COMPREHENSIVE TECHNOLOGY CENTRE OF FOSHAN CUSTOMS

检 测 报 告
TEST REPORT

GB/T 4100-2015 《陶瓷砖》附录 G 干压陶瓷砖（$E \leq 0.5\%$ BⅠa类）

条款 Clause	性能 Properties	检验方法 Test Method	要求 Requirements	检验结果 Results	判定 Verdicts
表 G.1 Table G.1	**物理性能** **Physical properties**				
	吸水率 质量分数 **Water absorption** Percent mass fraction	GB/T 3810.3-2016	$E \leq 0.5\%$	0.10%	P
			单个值不大于 0.6% Individual maximum 0.6%	0.08%～0.12%	P
	耐磨性 **Abrasion resistance** 用于地面的有釉砖的表面耐磨性 Resistance to surface abrasion of glazed tiles intended for use on floors	GB/T 3810.7-2016	报告耐磨级别 Report abrasion class	4 级 Class 4	—
			报告耐磨转数 Report cycles passed	2100	—
	静摩擦系数 **Static coefficient of friction**	附录 M Annex M	单个值≥0.50 Individual≥0.50	干法 Dry: 0.50～0.52	P
	化学性能 **Chemical properties**				
	耐化学腐蚀性 Resistance to chemicals				
	耐家庭化学试剂和游泳池盐类 Resistance to household chemicals and swimming pool salts				
	a) 家庭化学试剂：氯化铵溶液，100g/L a) Household chemicals: Ammonium chloride, 100g/L	GB/T 3810.13-2016	不低于 GB Minimum GB	GA	P
	b) 游泳池盐类：次氯酸钠溶液，20mg/L b) Swimming pool salts: Sodium hypochlorite solution, 20mg/L	GB/T 3810.13-2016	不低于 GB Minimum GB	GA	P
	耐低浓度酸和碱 Resistance to low concentrations of acids and alkalis				
	a) 3%盐酸溶液(v/v) a) Hydrochloric acid solution, 3% (v/v)	GB/T 3810.13-2016	制造商应报告等级 Manufacturer to state classification	GLA	—
	b) 柠檬酸溶液，100g/L b) Citric acid solution, 100g/L	GB/T 3810.13-2016	制造商应报告等级 Manufacturer to state classification	GLA	—
	c) 氢氧化钾溶液，30g/L c) Potassium hydroxide, 30g/L	GB/T 3810.13-2016	制造商应报告等级 Manufacturer to state classification	GLB	—
	耐高浓度酸和碱 Resistance to high concentrations of acids and alkalis				
	a) 18%盐酸溶液(v/v) a) Hydrochloric acid solution, 18% (v/v)	GB/T 3810.13-2016	报告检验结果 Test method available	GHA	—
	b) 5 %乳酸溶液(v/v) b) Lactic acid, 5 % (v/v)	GB/T 3810.13-2016	报告检验结果 Test method available	GHA	—
	c) 氢氧化钾溶液，100g/L c) Potassium hydroxide, 100g/L	GB/T 3810.13-2016	报告检验结果 Test method available	GHB	—

检 测 报 告
TEST REPORT

用语说明 Possible test case verdicts
1. P(ass)：合格 *Test item does meet the requirement.*
2. F(ail)：不合格 *Test item does not meet the requirement.*
3. —：未进行判定 *Verdict was not carried out.*
4. N/A：不适用 *Test case does not apply to the test item.*

*** ***

报告结束 End of Test Report