中国认可
国际互认
检测
TESTING
CNAS L1978

190000122473

检 测 报 告
TEST REPORT

报 告 编 号:
REPORT NO. : 25201904786

样 品 名 称: 釉面砖
NAME OF SAMPLE: PORCELAIN TILES

委 托 单 位: 佛山市嘉欣华陶瓷有限公司
APPLICANT: FOSHAN KIVA CERAMICS CO.,LTD

检 验 日 期:
DATE OF TEST: 25/10/2023 – 07/11/2023 (dd/mm/yy)

国 家 建 筑 卫 生 陶 瓷 检 测 重 点 实 验 室
STATE KEY TESTING LABORATORY OF BUILDING CERAMICS AND SANITARY WARE
佛山出入境检验检疫局检验检疫综合技术中心
INSPECTION AND QUARANTINE COMPREHENSIVE TECHNOLOGY CENTRE
OF FOSHAN ENTRY-EXIT INSPECTION & QUARANTINE BUREAU

佛山出入境检验检疫局检验检疫综合技术中心

INSPECTION AND QUARANTINE COMPREHENSIVE TECHNOLOGY CENTRE OF FOSHAN ENTRY-EXIT INSPECTION & QUARANTINE BUREAU

检测报告

TEST REPORT

样品名称 Name of sample	釉面砖 PORCELAIN TILES	名义尺寸 Nominal size (N)	1200mm×600mm
表面特性 Nature of the surface	有釉 Glazed (GL)	工作尺寸 Work size (S_w)	1200mm×600mm×10.9mm
类别 Group	B Ⅰa 类，磨边砖 Group B Ⅰa, rectified tiles	样品描述 Description of Samples	样品完好,适合测试 The samples are sound, intact and fit for test.
样品标记 Mark of samples	—	样品数量 Quantity of samples	30 块 30 Pieces
委托单位 Applicant	佛山市嘉欣华陶瓷有限公司 FOSHAN KIVA CERAMICS CO.,LTD	委托单位地址 Address of applicant	佛山市三水区西南街道 左田民营开发区（F6） (F6) SADA PRIVATE DEVELOPMENT AREA, SOUTHWEST OF RIVER STREET, SANSHUI DISTRICT,FOSHAN CITY, GUANGDONG,CHINA.
委托单位电话 Telephone of applicant	86-13927243664	委托单位传真 Fax of applicant	—
样品来源 Source of Samples	委托单位自送样品 Samples selected by applicant	接样日期 Received on	25/10/2023
检验依据 Test Standard	SASO ISO 13006:2018 *Ceramic tiles – Definitions, classification, characteristics and marking* Annex G Dry-pressed ceramic tiles with low water absorption $E_v \leq 0,5$ % Group B Ⅰa		
检验结论 Conclusion of Test	样品经检验,所检验项目的检验结果符合 SASO ISO 13006:2018 标准中附录 G 的规定。 The results conform to the requirement of Annex G of standard SASO ISO 13006:2018 with respect to the test items.		
检验单位盖章 Stamp of Test Unit	日期：11/11/2023 Date:	检验单位联系方式 Address of Test Unit	地址：广东省佛山市禅城区魁奇一路澜石（国际）金属交易中心十八座二楼 Address : 2/F, Building 18, Lanshi International Metal Exchange Center, Kuiqiyi Road, Chancheng District, Foshan, Guangdong, China (528000) 电话（Tel）：86-757-83960558 86-757-83827991 传真（Fax）：86-757-83827971 邮箱（E-mail）：fsiqtc@163.com 网址（url）：http://www.fsiqtc.com/
声明 Notes	1、我们已尽所知所能实施上述检验，不能因签发本报告而免除有关各方根据合同和法律所承担的责任和义务： All inspections are carried out conscientiously to the best of our knowledge and ability. This report does not in any respect absolve the other related parties from his contractual and legal obligations. 2、未经本实验室书面许可，不得部分复制本报告； This report shall not be reproduced, except in full, without the prior written approval from the issuing laboratory. 3、本报告仅是样品的检测结果。 The results in this report apply to the samples only.		

检验 Tested by 杨明多　审核 Inspected by 钟江伟　批准 Approved by 肖永江

委托单位声明 Remark of applicant
品牌 Brand: KIVA 生产单位: 佛山市嘉欣华陶瓷有限公司 Manufacturer: FOSHAN KIVA CERAMICS CO.,LTD 生产单位地址: 佛山市三水区西南街道左田民营开发区（F6） Address of Manufacturer: (F6) SADA PRIVATE DEVELOPMENT AREA, SOUTHWEST OF RIVER STREET,SANSHUI DISTRICT,FOSHAN CITY, GUANGDONG,CHINA.

SASO ISO 13006:2018 *Ceramic tiles – Definitions, classification, characteristics and marking*

条款 Clause	性能 Properties	检验方法 Test Method	要求 Requirements		检验结果 Results	判定 Verdicts
附录 G 表 G.1 Annex G Table G.1	**尺寸和表面质量 Dimensions and surface quality**					
	长度 Length 每块砖的平均尺寸相对于工作尺寸的允许偏差 The deviation,of the average size for each tile (2 sides) from the work size	SASO ISO 10545-2/2016	N≥15cm	±0.3%	-0.03%~-0.02%	P
				±1.0mm	-0.4mm~-0.2mm	P
	宽度 Width 每块砖的平均尺寸相对于工作尺寸的允许偏差 The deviation,of the average size for each tile (2 sides) from the work size	SASO ISO 10545-2/2016	N≥15cm	±0.3%	+0.02%~+0.06%	P
				±1.0mm	+0.2mm~+0.4mm	P
	厚度 Thickness 每块砖厚度的平均值相对于工作尺寸的最大允许偏差 The deviation of the average thickness of each tile from the work size thickness	SASO ISO 10545-2/2016	N≥15cm	±5%	-0.6%~+0.4%	P
				±0.5mm	-0.1mm~0	P
	边直度 Straightness of sides 相对于工作尺寸的最大允许偏差 The maximum deviation from straightness related to the corresponding work sizes					
	长度 length	SASO ISO 10545-2/2016	N≥15cm	±0.3%	0~+0.01%	P
				±0.8mm	0~+0.1mm	P
	宽度 Width	SASO ISO 10545-2/2016	N≥15cm	±0.3%	0~+0.01%	P
				±0.8mm	0~+0.1mm	P
	直角度 Rectangularity 相对于工作尺寸的最大允许偏差 The maximum deviation from Rectangularity related to the corresponding work sizes					
	长度 length	SASO ISO 10545-2/2016	N≥15cm	±0.3%	-0.05%~-0.03%	P
				±1.5mm	-0.6mm~-0.4mm	P
	宽度 Width	SASO ISO 10545-2/2016	N≥15cm	±0.3%	+0.04%~+0.06%	P
				±1.5mm	+0.2mm~+0.3mm	P
	表面平整度: 最大允许偏差 Surface flatness: The maximum deviation from flatness					
	a)对于由工作尺寸计算的对角线的中心弯曲度 a) centre curvature, related to diagonal calculated from the work size;	SASO ISO 10545-2/2016	N≥15cm	±0.4%	-0.06%~-0.04%	P
				±1.8mm	-0.8mm~-0.5mm	P

SASO ISO 13006:2018 *Ceramic tiles – Definitions, classification, characteristics and marking*

条款 Clause	性能 Properties	检验方法 Test Method	要求 Requirements		检验结果 Results	判定 Verdicts
附录 G 表 G.1 Annex G Table G.1	b)对于由工作尺寸计算的边弯曲度 b) edge curvature, related to the corresponding work sizes;					
	长度 length	SASO ISO 10545-2/2016	N≥15cm	±0.4%	+0.01%~+0.02%	P
				±1.8mm	+0.1mm~+0.2mm	P
	宽度 Width	SASO ISO 10545-2/2016	N≥15cm	±0.4%	-0.11%~-0.08%	P
				±1.8mm	-0.7mm~-0.4mm	P
	c)对于由于工作尺寸计算的对角线的翘曲度 c) warpage, related to diagonal calculated from the work size.	SASO ISO 10545-2/2016	N≥15cm	±0.4%	+0.02%~+0.03%	P
				±1.8mm	+0.3mm~+0.4mm	P
	表面质量 **Surface quality**	SASO ISO 10545-2/2016	至少有 95%的砖其主要区域无明显缺陷 A minimum of 95% of the tiles shall be free from visible defects inspected vertically at 1.0m.		100%	P
	物理性能 **Physical properties**					
	吸水率 质量分数 **Water absorption** Percent mass fraction	SASO ISO 10545-3/2018	E_v≤0.5%		0.06%	P
			单个值不大于 0.6% Individual maximum 0.6%		0.05%~0.08%	P
	破坏强度/N **Breaking strength, in N**	SASO ISO 10545-4/2016	⩾1300		2715	P
	断裂模数/(N/mm²) **Modulus of rupture, in N/mm²** 不适用于破坏强度≥ 3000N 的陶瓷砖 Not applicable to tiles with breaking strength ≥ 3000N	SASO ISO 10545-4/2016	平均值⩾35 Minimum 35		37.9	P
			单个值⩾32 Individual minimum 32		35.8~39.6	P
	抗冲击：恢复系数 **Impact resistance:** Coefficient of restitution (COR)	SASO ISO 10545-5/2006	报告检验结果 Test method available		0.87	—
	耐磨性 **Abrasion resistance** 用于地面的有釉砖的表面耐磨性 Resistance to surface abrasion of glazed tiles intended for use on floors	SASO ISO 10545-7/2007	报告耐磨级别 Report abrasion class		4 级 Class 4	—
			报告耐磨转数 Report cycles passed		2100	—
	线性热膨胀系数：室温~100℃ **Coefficient of linear thermal expansion**: from ambient temperature to 100℃	SASO ISO 10545-8/2016	报告检验结果 Test method available		$6.5\times10^{-6}℃^{-1}$	—
	抗热震性 **Thermal shock resistance**	SASO ISO 10545-9/2016	报告检验结果 Test method available		样品经试验，无炸裂或裂纹 Fully resistance	—
	湿膨胀/(mm/m) **Moisture expansion, in mm/m**	SASO ISO 10545-10/2006	报告检验结果 Test method available		<0.06	—

SASO ISO 13006:2018 *Ceramic tiles – Definitions, classification, characteristics and marking*

条款 Clause	性能 Properties	检验方法 Test Method	要求 Requirements	检验结果 Results	判定 Verdicts
附录 G 表 G.1 Annex G Table G.1	**抗釉裂性：**有釉砖 **Crazing resistance:** glazed tiles	SASO ISO 10545-11/2007	应通过此项测试 Required	样品经试验，无裂纹或剥落 Fully resistance	P
	抗冻性 Frost resistance	SASO ISO 10545-12/2007	报告检验结果 Test method available	所有样品无裂纹或破损 Fully resistance	P
	化学性能 Chemical properties				
	耐污染性 Resistance to staining				
	a)轻油中的铬绿 a) Green staining agent in light oil	SASO ISO 10545-14/2016	不低于 3 级 Minimum Class 3	5 级 Class 5	P
	b)轻油中的红色污染物 b) Red staining agent in light oil	SASO ISO 10545-14/2016	不低于 3 级 Minimum Class 3	5 级 Class 5	P
	c) 13g/L 碘酒液 c) Iodine, 13g/L solution in alcohol	SASO ISO 10545-14/2016	不低于 3 级 Minimum Class 3	5 级 Class 5	P
	d)橄榄油 d) Olive oil	SASO ISO 10545-14/2016	不低于 3 级 Minimum Class 3	5 级 Class 5	P
	耐化学腐蚀性 Resistance to chemicals				
	耐家庭化学试剂和游泳池盐类 Resistance to household chemicals and swimming pool salts				
	a) 家庭化学试剂：氯化铵溶液，100g/L a) Household chemicals: Ammonium chloride, 100g/L	SASO ISO 10545-13/2018	不低于 B Minimum B	A	P
	b) 游泳池盐类：次氯酸钠溶液，20mg/L b) Swimming pool salts: Sodium hypochlorite solution, 20mg/L	SASO ISO 10545-13/2018	不低于 B Minimum B	A	P
	耐低浓度酸和碱 Resistance to low concentrations of acids and alkalis				
	a) 3%盐酸溶液(v/v) a) Hydrochloric acid solution, 3% (v/v)	SASO ISO 10545-13/2018	制造商应声明等级 Manufacturer to state classification	LA	—
	b) 柠檬酸溶液，100g/L b) Citric acid solution, 100g/L	SASO ISO 10545-13/2018	制造商应声明等级 Manufacturer to state classification	LA	—
	c) 氢氧化钾溶液，30g/L c) Potassium hydroxide, 30g/L	SASO ISO 10545-13/2018	制造商应声明等级 Manufacturer to state classification	LA	—
	耐高浓度酸和碱 Resistance to high concentrations of acids and alkalis				
	a) 18%盐酸溶液(v/v) a) Hydrochloric acid solution, 18% (v/v)	SASO ISO 10545-13/2018	报告检验结果 Test method available	HA	—
	b) 5 %乳酸溶液(v/v) b) Lactic acid, 5 % (v/v)	SASO ISO 10545-13/2018	报告检验结果 Test method available	HA	—
	c) 氢氧化钾溶液，100g/L c) Potassium hydroxide, 100g/L	SASO ISO 10545-13/2018	报告检验结果 Test method available	HA	—

SASO ISO 13006:2018 *Ceramic tiles – Definitions, classification, characteristics and marking*

条款 Clause	性能 Properties	检验方法 Test Method	要求 Requirements	检验结果 Results	判定 Verdicts
附录 G 表 G.1 Annex G Table G.1	**铅镉溶出量 Lead and Cadmium release**				
	a)铅溶出量/(mg/dm^2) a) Lead release, in mg/dm^2	SASO ISO 10545-15/2006	报告检验结果 Test method available	＜0.01	—
	b)镉溶出量/(mg/dm^2) b) Cadmium release, in mg/dm^2	SASO ISO 10545-15/2006	报告检验结果 Test method available	＜0.002	—

用语说明 Possible test case verdicts
1. P(ass)：合格 *Test item does meet the requirement.*
2. F(ail)：不合格 *Test item does not meet the requirement.*
3. —：未进行判定 *Verdict was not carried out.*
4. N/A：不适用 *Test case does not apply to the test item.*

*** ***

报告结束 End of Test Report